(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 15 July 2004 (15.07.2004)

PCT

(10) International Publication Number WO 2004/059028 A1

(51) International Patent Classification7:

C23C 2/06

[KR/KR]; 312-6 Suksu-Dong Manan-Gu, Anyang-Si Gyunggi-Do 430-040 (KR).

(21) International Application Number:

PCT/KR2003/000901

(74) Agent: KIM, Ki-Ryung; King Road Ptlf, Suite 3111, Hyundai 41 Tower, 917-9 Mok-1-Dong, Yangchun-GU, Seoul 158-723 (KR).

(84) Designated States (regional): European patent (AT, BE,

IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,

(22) International Filing Date:

7 May 2003 (07.05.2003)

Korean

(25) Filing Language:

(26) Publication Language:

English

(30) Priority Data: 10-2002-0083330

24 December 2002 (24.12.2002) KR

Declaration under Rule 4.17:

 as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

(71) Applicant (for all designated States except US): PUNG KUK EDM WIRE MANUFACTURING CO., LTD [KR/KR]; 404-8 Nojang-Ri Jundong-Myun, Yungi-Gun, Chungchungnam-Do 339-841 (KR).

Published:

with international search report


(81) Designated States (national): JP, US.

(72) Inventor; and

(75) Inventor/Applicant (for US only): LEE, Jong-Cho

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD OF MANUFACTURING ZINC-COATED ELECTRODE WIRE FOR ELECTRIC DISCHARGE PROCESSORS USING HOT DIP GALVANIZING PROCESS



(57) Abstract: Disclosed is a method of manufacturing a zinccoated electrode wire for electro discharge machining using a hot
dip galvanizing process. The method includes firstly surface-forming a wire (1) in such a way that its terminal end is tapered while
the wire is drawn through a first die at step 10, pre-coating zinc
around the firstly processed wire in a molten zinc bath (2) at step
20, main-coating the pre-coated wire with zinc (3) using a sizing
die before zinc pre-coated on the wire is hardened at step 30, secondly surface-forming the main-coated wire in such a way that zinc
coated around the wire has a uniform thickness using a second die
having a smaller diameter than the wire at step 40, heat-treating
the secondly surface-processed wire at step 50, and drawing the
heat-treated wire using a third die (5) made of natural diamond at
step 60.